





**Internal transmittance  $\tau_i$  at reference thickness  $d$  [mm] = 2**  
**The internal transmittance values, tabulated and graphically represented, are reference values only**

$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$
200	< 1.0E-05	500	9.9E-01	800	1.0E+00	1100	1.0E+00	2200	9.7E-01	3700	2.0E-01
210	< 1.0E-05	510	9.9E-01	810	1.0E+00	1110	1.0E+00	2250	9.7E-01	3750	2.2E-01
220	< 1.0E-05	520	9.9E-01	820	1.0E+00	1120	1.0E+00	2300	9.7E-01	3800	2.4E-01
230	< 1.0E-05	530	9.9E-01	830	1.0E+00	1130	1.0E+00	2350	9.7E-01	3850	2.4E-01
240	< 1.0E-05	540	1.0E+00	840	1.0E+00	1140	1.0E+00	2400	9.6E-01	3900	2.2E-01
250	< 1.0E-05	550	1.0E+00	850	1.0E+00	1150	1.0E+00	2450	9.6E-01	3950	2.0E-01
260	< 1.0E-05	560	1.0E+00	860	1.0E+00	1160	1.0E+00	2500	9.5E-01	4000	1.9E-01
270	< 1.0E-05	570	1.0E+00	870	1.0E+00	1170	1.0E+00	2550	9.4E-01	4050	1.7E-01
280	< 1.0E-05	580	1.0E+00	880	1.0E+00	1180	1.0E+00	2600	9.4E-01	4100	1.5E-01
290	< 1.0E-05	590	1.0E+00	890	1.0E+00	1190	1.0E+00	2650	9.3E-01	4150	1.3E-01
300	9.6E-03	600	1.0E+00	900	1.0E+00	1200	1.0E+00	2700	8.5E-01	4200	1.1E-01
310	1.6E-01	610	1.0E+00	910	1.0E+00	1250	1.0E+00	2750	4.0E-01	4250	8.4E-02
320	5.1E-01	620	1.0E+00	920	1.0E+00	1300	1.0E+00	2800	3.3E-01	4300	6.0E-02
330	7.7E-01	630	1.0E+00	930	1.0E+00	1350	1.0E+00	2850	3.6E-01	4350	3.9E-02
340	9.0E-01	640	1.0E+00	940	1.0E+00	1400	1.0E+00	2900	3.9E-01	4400	2.2E-02
350	9.5E-01	650	1.0E+00	950	1.0E+00	1450	1.0E+00	2950	4.1E-01	4450	1.0E-02
360	9.7E-01	660	1.0E+00	960	1.0E+00	1500	1.0E+00	3000	4.2E-01	4500	4.0E-03
370	9.8E-01	670	1.0E+00	970	1.0E+00	1550	1.0E+00	3050	4.2E-01	4550	1.3E-03
380	9.9E-01	680	1.0E+00	980	1.0E+00	1600	1.0E+00	3100	4.2E-01	4600	4.1E-04
390	9.9E-01	690	1.0E+00	990	1.0E+00	1650	1.0E+00	3150	4.2E-01	4650	1.2E-04
400	9.9E-01	700	1.0E+00	1000	1.0E+00	1700	1.0E+00	3200	4.1E-01	4700	4.2E-05
410	9.9E-01	710	1.0E+00	1010	1.0E+00	1750	1.0E+00	3250	4.0E-01	4750	1.4E-05
420	9.9E-01	720	1.0E+00	1020	1.0E+00	1800	1.0E+00	3300	3.9E-01	4800	< 1.0E-05
430	9.9E-01	730	1.0E+00	1030	1.0E+00	1850	1.0E+00	3350	3.7E-01	4850	< 1.0E-05
440	9.9E-01	740	1.0E+00	1040	1.0E+00	1900	1.0E+00	3400	3.5E-01	4900	< 1.0E-05
450	9.9E-01	750	1.0E+00	1050	1.0E+00	1950	9.9E-01	3450	3.1E-01	4950	< 1.0E-05
460	9.9E-01	760	1.0E+00	1060	1.0E+00	2000	9.9E-01	3500	2.7E-01	5000	< 1.0E-05
470	9.9E-01	770	1.0E+00	1070	1.0E+00	2050	9.9E-01	3550	2.3E-01	5050	< 1.0E-05
480	9.9E-01	780	1.0E+00	1080	1.0E+00	2100	9.8E-01	3600	2.1E-01	5100	< 1.0E-05
490	9.9E-01	790	1.0E+00	1090	1.0E+00	2150	9.8E-01	3650	2.0E-01	5150	< 1.0E-05